PRODUCT DATA SHEET

PRODUCT DESCRIPTION: Flexible Magnetic Sheeting with Outdoor Gloss/Matt White PVC Film

STANDARD THICKNES: 0.5mm, 0.6mm, 9 mm (Vehicle grade) (+-0.05mm)

STANDARD WIDTH: 620mm,1000mm,1020mm, 1270mm (+3mm/-0)

STANDARD LENGTH: 10M, 20M, 30M (+0.5M/-0)

MAGNETIC PROPERTIES

Maximum Energy Product: 0.65 to 0.75 MGOe

Remanence: 1600-1900 G

Coercivity: 1200-1500 Oe

Intrinsic Coercivity: 2200-2500 Oe

MAGNETIC POLE WIDTH AND MAGNETIC PULL

Magnetic Pole Width: 2.0mm

Magnetic Pull (g/cm²)
≥ 8
≥ 17
≥ 24
≥ 30
≥ 55
≥ 41
≥ 47
≥ 67

PHYSICAL PROPERTIES

Flexibility: can be wrapped around a rod with a 12mm radius at 20°C without cracking

Specific Gravity: 3.5 to 3.7 g/cm³

Cutting: Scissor cutting, knife-cutting, die-cutting, and slitting can be done with ease.

TEMPERATURE RESISTANCE

End-use temperature range: - 30°C / + 55°C

Short term resistance: 65°C

BACKCOATING: The magnetic sheeting has a UV hardened coating on the magnetic side.

PVC FILM

Outdoor Applications: 2-year durability under Middle European exposure conditions. Exposure to severe humidity, ultra-violet light or conditions found in tropical, subtropical or desert regions will cause a more rapid deterioration.

Printability:

Digital	Printing: Solvent-based Inks	Yes
Digital	Printing: UV Cure Inks	Yes
Conventional Offset Printing		Yes

Notes:

- Thickness refers to thickness of magnetic sheeting only. It does not include thickness of PVC film. Thickness of PVC film is 0.10mm.
- 2. Screen Printability with UV cure inks deteriorates with time. We strongly recommend users to use the product within 6 months after date of production when screen print with UV inks is involved in the application.

Sanders Group: Industriepark 3 5663 PG Geldrop The Netherlands www.sandersgroup.eu

Magnetic Solutions Ltd. Unit 15c Tinsley Industrial Estate Shepcote Lane Sheffield S9 1TH United Kingdom www.magnetic-solutions-ltd.co.uk

Aiman GZ Parque Empresarial Neinor Henares Edificio 7 – Nave 14 28880 Meco – Madrid Spain www.aimangz.es

SANDERS